

Cont  
AI  
JIS-C hardness at a distance of 15 mm from the center point of the inner core is higher than the center hardness by 5 to 20,

the outer core has a thickness of 0.3 to 2.0 mm and a surface hardness in JIS-C hardness of 75 to 90, and is formed from press molded rubber composition comprising polybutadiene, a co-crosslinking agent, an organic peroxide and a filler, and the surface hardness of the outer core is higher than the center hardness of the inner core by 15 to 30, and

the cover is formed from a combination of ionomer resin and at least one of thermoplastic elastomer or diene block copolymer, and the outmost cover layer has a thickness of 1.5 to 2.5 mm and a surface hardness in Shore D hardness of 64 to 72.

---